

TECHNICAL DATA SHEET



| Product name | Revised |
|---------------------|------------|
| GENAN COARSE POWDER | 22.02.2019 |

| Product description |
|--|
| Free-flowing, homogenous and uniform, black rubber powder derived from end-of-life tyres through granulation and cleaning. |

| Contact Data of Manufacturer | | | | | |
|------------------------------|---|---|---|--|---|
| Plant: | Genan A/S Jegindøvej 16 DK-8800 Viborg Denmark | Genan GmbH Gottlieb-Daimler Straße 34 D-46282 Dorsten Germany | Betriebsstätte Oranienburg: Birkenallee 80 D-16515 Oranienburg Germany | Betriebsstätte Kammlach: Im Gewerbepark Unterallgäu 1 D-87754 Kammlach Germany | Genan Inc. 18038 Beaumont Hwy. Houston TX77049 USA |
| Telephone: | +45 8728 3000 | +49 2362 9527 0 | +49 3301 578 0 | +49 8261 7369 0 | +1 713 6748500 |
| Fax: | | +49 2362 9257 150 | +49 3301 578 150 | +49 8261 7369 150 | +1 713 6748501 |
| E-mail: | genan@genan.eu | | | | genan@genan.us |

| Typical properties | | | | |
|--|---------------------|-------------------|---------------|----------------|
| Properties | Test methods | Unit | Specification | Typical values |
| Specific gravity | ASTM D1817-05(2016) | kg/m ³ | 1.100-1.200 | 1.160 |
| Bulk density | EN 1097-3:1998 | kg/m ³ | 355 ±8% | 355 |
| Particle size range | ISO 13322-2:2006 | mm | 0,5-0,8 | 0,5-0,8 |
| Total polymer content (RCH) | ISO 9924-3:2009 | % | ≥ 40 | 45 |
| Natural rubber content | ASTM D 297, 52-53 | % | 10-35 | 10-35 |
| Ash content | ISO 9924-3:2009 | % | < 15 | 8 |
| Carbon black | ASTM D 297, 38-39 | % | 25-40 | 32-36 |
| Acetone extractable | ASTM D 297, 17-19 | % | 10-20 | 11-17 |
| Moisture content (Loss: 2h @ 105°C) | ASTM D1509 - 15 | % | ≤ 1 | < 1 |
| Free metal content | OA-698: (Note 1) | % | ≤ 0,004 | ≤ 0,002 |
| Free fibre content | OA-698: (Note 1) | % | ≤ 0,002 | < 0,001 |
| Content of coloured rubber particles | OA-698: (Note 1) | % | ≤ 0,1 | < 0,04 |
| PAH 8 REACH | AfPS GS 2014:01 PAK | mg/kg | ≤ 20 | < 15 |
| <i>Note 1: Non-standardized test method "Determination of bulk density and free impurities in rubber powder and granulate", which your Genan representative will forward upon request. This test method is chosen as values obtained from the use of ASTM 5603 are below the detection limits.</i> | | | | |

| Remarks | |
|-----------------------------|---|
| Particle size distribution: | Information on the actual particle size distribution is available on the relevant sieve curves, which may be downloaded from the Genan website at any time. |
| Health & Safety: | Guidelines on health and safety are stated in the relevant Safety Data Sheet, which may be downloaded from the Genan website at any time. |

Characteristics stated are typical for the product. The product is derived from a large number of different tyres; consequently, Genan cannot give any exact values on the chemical composition of the material. The above-mentioned characteristics and values have been prepared to the best of our knowledge, and Genan shall not be liable for any insufficiency or inaccuracy in such information.

| CERTIFICATIONS | Genan A/S | Genan GmbH | Genan Inc. |
|----------------|---|---|---------------------------------|
| | ISO 9001:2015 ISO 14001:2015 ISO 50001:2011 | ISO 9001:2015 ISO 14001:2015 ISO 50001:2011 OHSAS 18001:2007 (Dorsten) | ISO 9001:2015 ISO 14001:2015 |