

TECHNICAL DATA SHEET



| | |
|----------------------------------|----------------|
| Product name | Revised |
| GENAN COATED INFILL NATURE GREEN | 01.05.2022 |

Product description
Free-flowing, homogeneous and uniform rubber granulate, derived from end-of-life tyres through granulation and cleaning - and colour-coated with inert, non-toxic pigments and polyurethane binder.

| Contact Data of Manufacturer | | | | | | |
|------------------------------|---|---|---|--|--|---|
| Plant: | Genan A/S Jegindøvej 16 DK-8800 Viborg Denmark | Genan GmbH Gottlieb-Daimler Straße 34 D-46282 Dorsten Germany | Betriebsstätte Oranienburg: Birkenallee 80 D-16515 Oranienburg Germany | Betriebsstätte Kammlach: Im Gewerbepark Unterallgäu 1 D-87754 Kammlach Germany | Genan, S.A. Lugar da Pardala Estrada Nacional 109, Km 31 PT-3880-728 São João de Ovar Portugal | Genan Inc. 18038 Beaumont Hwy. Houston TX77049 USA |
| Tel: | +45 8728 3000 | +49 2362 9527 0 | +49 3301 578 0 | +49 8261 7369 0 | +351 256 580 600 | +1 713 6748500 |
| Fax: | | +49 2362 9257 150 | +49 3301 578 150 | +49 8261 7369 150 | | +1 713 6748501 |
| E-mail: | info-dk@genan.com | info-de@genan.com | | | info-pt@genan.com | info-us@genan.com |

| Typical properties | | | | |
|-------------------------------------|---|-------------------|---|---|
| Properties | Test methods | Unit | Specification | Typical values |
| Specific density | ASTM D1817-05(2016) | kg/m ³ | 1.100-1.200 | 1.160 |
| CIELAB colour code (Note 2) | EN ISO 11664-4 "Colorimetry - Part 4: CIE 1976 L*a*b* Colour space" | n/a | L*: 27,50 a*: -13,70 b*: 3,20 ΔE < 3 | L*: 27,50 a*: -13,70 b*: 3,20 ΔE < 2 |
| UVA resistance (340 nm) | EN 14836 / EN 20105-A02 | n/a | > 3 | 3 |
| UVB resistance (313 nm) | EN 14836 / EN 20105-A02 | n/a | > 3 | 3 |
| Bulk density | EN 1097-3:1998 | kg/m ³ | 455 ±8% | 455 |
| Particle size range | ISO 13322-2:2006 | mm | 0,8-3,0 | 0,8-3,0 |
| | EN 15330-1 / FIFA | mm | 1,0-2,5 | 1,0-2,5 |
| Particle Size < 0,5 mm | DIN 53477:1992-11 | % | < 1,0 | 0,25 |
| Total polymer content (RCH) | ISO 9924-3:2009 | % | > 40 | 45 |
| Ash content | ISO 9924-3:2009 | % | < 15 | 8 |
| Moisture content (Loss: 2h @ 105°C) | ASTM D1509 - 15 | % | < 1 | < 1 |
| Free metal content | OA-698; (Note 1) | % | < 0,004 | < 0,002 |
| Free fibre content | OA-698; (Note 1) | % | < 0,002 | < 0,001 |
| Other contamination | OA-698; (Note 1) | % | < 0,004 | < 0,002 |
| Inhalable dust classification | EN 15051-2:2013+A1:2016 | | Very low to low | Very low |
| PAH 8 REACH | AfPS GS 2019:01 PAK | mg/kg | < 20 | < 15 |

Note 1: Non-standardized test method "Determination of bulk density and free impurities in rubber powder and granulate", which your Genan representative will forward upon request. This test method is chosen as values obtained from the use of ASTM D5603 are below the detection limits.

Note 2: L*a*b* colour code defined with an annually calibrated Konica Minolta CM5 spectrophotometer.

| Remarks | |
|----------------------------|---|
| DIN 18035-7:2019 | GENAN COATED INFILL complies with all requirements in relation to migration according to DIN 18035-7:2019. |
| EN 71-3:2019 | GENAN COATED INFILL complies with all requirements according to EN 71-3:2019_Safety of Toys - Part 3: Migration of certain elements. |
| PAH 8 REACH | A material sample has been extracted in accordance with EN 17409:2019, and the result is presented as a moving average of the 4 most recent analyses. |
| International standards | GENAN COATED INFILL complies with all requirements for infill according to FIFA 2015, World Rugby 2016 and EN15330-1:2013. |
| National standards | GENAN COATED INFILL complies with all requirements for infill according to NF P90-112. |
| Particle size distribution | Information on the actual particle size distribution is available on the relevant sieve curves, which may be downloaded from the Genan website at any time. |
| Abrasion resistance | GENAN COATED INFILL is intended for use as infill material in artificial turf only. Friction may cause colour-coating to wear off. |
| Health & Safety | Guidelines on health and safety are stated in the relevant Safety Data Sheet, which may be downloaded from the Genan website at any time. |

Characteristics stated are typical for the product. The product is derived from a large number of different tyres; consequently, Genan cannot give any exact values on the chemical composition of the material. The above-mentioned characteristics and values have been prepared to the best of our knowledge, and Genan shall not be liable for any insufficiency or inaccuracy in such information.

| CERTIFICATIONS | Genan A/S | Genan GmbH | Genan Inc. | Genan, S.A. |
|----------------|----------------|----------------|----------------|----------------|
| | ISO 9001:2015 | ISO 9001:2015 | ISO 9001:2015 | ISO 9001:2015 |
| | ISO 14001:2015 | ISO 14001:2015 | ISO 14001:2015 | ISO 14001:2015 |
| | ISO 45001:2018 | ISO 45001:2018 | ISO 45001:2018 | ISO 45001:2018 |
| | ISO 50001:2018 | ISO 50001:2018 | ISO 50001:2018 | ISO 50001:2018 |