

# TECHNICAL DATA SHEET



Product name	Revised
GENAN 40 Mesh	01.10.2024

Product description
Free-flowing, homogenous and uniform, black rubber powder derived from end-of-life tyres through cryogenic milling. As anti-caking agent, 0.5% SiO <sub>2</sub> (Ultrasil®VN3) is added.

Contact Data of Manufacturer						
Plant:	Genan A/S Jegindøvej 16 DK-8800 Viborg Denmark	Genan GmbH Gottlieb-Daimler Straße 34 D-46282 Dorsten Germany	Betriebsstätte Oranienburg: Birkenallee 80 D-16515 Oranienburg Germany	Betriebsstätte Kammlach: Im Gewerbepark Unterallgäu 1 D-87754 Kammlach Germany	Genan, S.A. Lugar da Pardala Estrada Nacional 109, Km 31 PT-3880-728 São João de Ovar Portugal	Genan Inc. 18038 Beaumont Hwy. Houston TX77049 USA
Tel.:	+45 8728 3000	+49 2362 9527 0	+49 3301 578 0	+49 8261 7369 0	+351 256 580 600	+1 713 6748500
Fax:		+49 2362 9257 150	+49 3301 578 150	+49 8261 7369 150		+1 713 6748501
E-mail:	info-dk@genan.com	info-de@genan.com			info-pt@genan.com	info-us@genan.com

Typical properties	Test methods	Unit	40 Mesh	40 Mesh	40 Mesh
			0-425 µm (V1)	125-425 µm (V2)	180-425 µm (V3)
Properties			Typical values	Typical values	Typical values
Specific density	ASTM D1817-05	kg/m <sup>3</sup>	1.160	1.160	1.160
Bulk density	EN 1097-3	kg/m <sup>3</sup>	475	435	460
Particle size range	ASTM D5644-01	µm	0-425	125-425	180-425
Particles > 425 µm (max. 10%)	ASTM D5644-01	%	< 1	< 1	< 1
Total polymer content (RCH)	ISO 9924-1	%	> 50	> 50	> 50
Ash content	ISO 9924-1	%	8	8	8
Carbon black	ISO 9924-1	%	30	30	30
Moisture content (Loss: 2h @ 105°C)	ASTM D1509-15	%	< 2	< 2	< 2
Impurities	Internal test method (Note 1)	%	<0,01	<0,01	<0,01
PAH 8 REACH	AfPS GS 2019:01 PAK	mg/kg	< 20	< 20	< 20

Note 1: The internal test method is based on Genan's expertise and on the international standards ASTM D5603-01 and EN14243-2.

Remarks	
Particle size distribution	Information on the actual particle size distribution is available on the relevant sieve curves, which can be downloaded from the Genan website. Alternatively, our sales department can forward upon request.
Impurities	GENAN 40 Mesh is a recycled product manufactured with end-of-life tyres as feedstock. Free impurities in the form of metal, textile, minerals, small stones, plastic and wood may thus occur.
Agglomeration	GENAN 40 Mesh may due to its physical properties - and depending on weather / storage conditions - have a tendency to cake over time. Storage as recommended in section 7.2 of the safety data sheet for this product.
Health & Safety	Guidelines on health and safety are stated in the relevant Safety Data Sheet, which can be downloaded from the Genan website. Alternatively, our sales department can forward upon request.

Characteristics stated are typical for the product. The product is derived from a large number of different tyres; consequently, Genan cannot give any exact values on the chemical composition of the material. The above-mentioned characteristics and values have been prepared to the best of our knowledge, and Genan shall not be liable for any insufficiency or inaccuracy in such information.

## CERTIFICATIONS

### Genan A/S

ISO 9001:2015  
ISO 14001:2015  
ISO 45001:2018  
ISO 50001:2018

### Genan GmbH

ISO 9001:2015  
ISO 14001:2015  
ISO 45001:2018  
ISO 50001:2018

### Genan Inc.

ISO 9001:2015  
ISO 14001:2015  
ISO 45001:2018  
ISO 50001:2018

### Genan, S.A.

ISO 9001:2015  
ISO 14001:2015  
ISO 45001:2018  
ISO 50001:2018